



MINISTRY OF AGRICULTURE, LIVESTOCK AND IRRIGATION
DEPARTMENT OF AGRICULTURE
RUBBER RESEARCH AND DEVELOPMENT CENTRE
NATURAL RUBBER TESTING LABORATORY

No.31Karbaraye Pagoda Road,
Mayangone Township,
Yangon, Myanmar.
Tel:+959421062962
Email: rrdc1234567@gmail.com



ISO/IEC 17025:2017
QAI/CA/TL/2024/0071

TEST REPORT

TR Sri. No ; 077
DATE ; 11.3.2025

TEST ORDER No / JOB No - TO-077/ L-25077
SAMPLE CODE - SN-077
SAMPLE NAME - RSS-1
SAMPLE MARK - -
SAMPLE AMOUNT - 1000g
SOURCE - Shwe Pin Le Co.,ltd
DATE IN - 25.2.2025
COMPLETED DATE - 11.3.2025

TEST RESULTS

ROOM TEMP: 25 °C

No	Test	Results	Method
1	DIRT (%) W/W	0.02	ISO 249
2	ASH (%) W/W	0.64	ISO 247-1
3	VOLATILE MATTER (%) W/W	0.74	ISO 248-1
4	NITROGEN (%) W/W	0.50	ISO 1656
5	PLASTICITY NO, P0	55.5	ISO 2007
6	PLASTICITY RETENTION INDEX, PRI	69	ISO 2930
7	LOVIBOND COLOR INDEX	9	ISO 4660
8	MOONEY VISCOSITY (ML (1+4) 100° C	82.5	ISO 289-1

APPROVED BY

Name : KYAW SOE THEIN
Position: SRAFF OFFICER